

The Eye Pad may be supplied sterile. When supplied sterile, it should be individually packaged. When more than one is contained in the same package, they should be interleaved with non-friable parchment.

Components Comply with the requirements for Absorbent Cotton and Absorbent Muslin as appropriate.

Weight of absorbent cotton Not less than 1.25 g per pad.

Foreign matter Not more than 1%, Appendix XI D.

Size available Cotton Eye Pads measuring 6.0 cm × 8.0 cm are usually available.

NON-EXTENSIBLE BANDAGES

Domette Bandage

Domette Bandage consists of union fabric of plain weave, in which the warp threads consist of cotton and the weft threads consist of wool. A light nap is raised on the woollen weft. The fabric is clean, reasonably free from weaving defects and contains not more than traces of leaf residue, seed coat and other impurities. It is in one continuous length with no joins. The edges are cut evenly, parallel with the warp threads, and are reasonably free from loose threads.

Fibre identification Complies with the tests for *wool* and *cotton*, Appendix XX A.

Content of wool Not less than 66.6% when determined by Method 2 of British Standard 4407:1975 (Methods of test. Quantitative analysis of fibre mixtures).

Threads per 10 cm Warp: 144 to 156, Appendix XX C1, Method II; weft: 81 to 91, Appendix XX C1, Method I.

Weight per unit area Not less than 100 g m⁻², Appendix XX D1, Method II.

Water-soluble and ether-soluble substances Carry out the methods for *water-soluble substances*, Appendix XX M, Method II, and for *ether-soluble substances*, Appendix XX N. The sum of the results is not more than 2.0%.

Open-wove Bandage

White Open-wove Bandage

Open-wove Bandage consists of fabric of plain weave, in which the warp threads consist of cotton and the weft threads consist of (a) cotton or (b) viscose or (c) combined cotton and viscose yarn, bleached to a good white and purified. It is practically odourless, reasonably free from weaving defects and contains not more than traces of leaf residue, seed coat and other impurities. It is in one continuous length.

The edges are cut evenly, parallel to the warp threads, and are reasonably free from loose threads. The warp yarn for Type 1 bandage has a count not finer than 15 tex and not coarser than 18 tex.

Fibre identification Complies with the tests for *cotton* or for both *cotton* and *viscose*, Appendix XX A.

Threads per 10 cm Complies with the appropriate requirements given in the Table. Use Method II of Appendix XX C1 for the warp and Method I of Appendix XX C1 for the weft.

Type number	Threads per 10 cm		Minimum weight per unit area g m ⁻²
	Warp	Weft	
1	155 to 187	100 to 114	64
2	135 to 163	84 to 96	33
3	107 to 129	73 to 83	28

Weight per unit area Complies with the appropriate requirement given in the Table, Appendix XX D1, Method II.

Water-soluble and ether-soluble substances Carry out the methods for *water-soluble substances*, Appendix XX M, Method II, and for *ether-soluble substances*, Appendix XX N. The sum of the results is not more than 1.50%.

Fluorescence When examined under ultra-violet light (365 nm) a layer about 5 mm in thickness may display only a slight brownish-violet fluorescence and a few yellow particles. Not more than a few isolated fibres show an intense blue fluorescence.

Labelling The label on the unit container, the label on the shelf container and the label on the outer transit container state whether the bandage complies with the requirements for Type 1 or for Type 2 or for Type 3 Open-wove Bandage.

In the absence of instructions to the contrary in the prescription or order, Type 1 Open-wove Bandage shall be supplied.

Unbleached Calico

Unbleached Calico consists of unbleached fabric of plain weave, in which the warp threads consist of cotton and the weft threads consist of cotton, of viscose or of combined cotton and viscose yarn. It is reasonably free from weaving defects and contains not more than traces of leaf residue, seed coat and other impurities.

Fibre identification Complies with the tests for *cotton* or for both *cotton* and *viscose*, Appendix XX A.

Threads per 10 cm Warp: 250 to 270; weft: 231 to 251, Appendix XX C1, Method II.

Weight per unit area Not less than 84 g m⁻², Appendix XX D1, Method III.

Water-soluble and ether-soluble substances Carry out the methods for *water-soluble substances*, Appendix XX M, Method II, and for *ether-soluble substances*, Appendix XX N. The sum of the results is not more than 10.0%.