

Content of zinc oxide in the adhesive mass Not less than 10.0%, Appendix XX Q.

Fibre identification After removal of the adhesive mass, complies with the tests for *cotton* or for both *cotton* and *viscose*, Appendix XX A.

Threads per 10 cm Warp: not less than 190, Appendix XX C1, Method III; weft: not less than 82, Appendix XX C2.

Weight of adhesive mass Not less than 120 g m⁻², Appendix XX D3, using Method II of Appendix XX D2.

Weight of fabric Not less than 110 g m⁻², Appendix XX D2, Method II.

Labelling If the tape has been dyed, the label on the unit container, the label on the shelf container and the label on the outer transit container state the colour of the final tape.

Impermeable Plastic Surgical Adhesive Tape

Waterproof Plastic Surgical Adhesive Tape; Waterproof Plastic Self-adhesive Plaster; Plastic Adhesive Strapping; Waterproof Strapping

Impermeable Plastic Surgical Adhesive Tape consists of an extensible waterproof plastic film spread evenly with an adhesive mass which does not offset when the tape is unrolled. The tape is supplied wound on spools or cores.

The film may be coloured with a suitable pigment.

The tape complies with the requirements stated under Adhesive Tapes and with the following requirements.

Weight of adhesive mass Not less than 30 g m⁻², Appendix XX D3, using Method III of Appendix XX D2.

Weight of film Not less than 65 g m⁻², Appendix XX D2, Method III.

Impermeable Plastic Surgical Synthetic Adhesive Tape

Waterproof Plastic Surgical Synthetic Adhesive Tape

Impermeable Plastic Surgical Synthetic Adhesive Tape consists of an extensible waterproof plastic film spread evenly with a polymeric adhesive mass which does not offset when the tape is unrolled. The tape is supplied wound on spools or cores.

The tape complies with the requirements stated under Adhesive Tapes and with the following requirements.

Water-vapour permeability Not more than 50 g m⁻² per 24 hours, Appendix XX J1.

Weight of adhesive mass Not less than 30 g m⁻², Appendix XX D3, using Method III of Appendix XX D2.

Weight of film Not less than 48 g m⁻², Appendix XX D2, Method III.

Permeable Non-woven Surgical Synthetic Adhesive Tape

Permeable Non-woven Synthetic Adhesive Tape

Permeable Non-woven Surgical Synthetic Adhesive Tape consists of a backing of a paper-based or non-woven textile material spread evenly with a polymeric adhesive mass which does not offset when the tape is unrolled and which does not separate from the backing under normal conditions of use. The tape is permeable to air and water vapour. It is supplied wound on spools or cores.

The tape complies with the requirements stated under Adhesive Tapes and with the following requirements.

Weight of backing material Not less than 34 g m⁻², Appendix XX D2, Method III.

Weight of adhesive mass Not less than 20 g m⁻², Appendix XX D3, using Method III of Appendix XX D2.

Permeable Plastic Surgical Adhesive Tape

Porous Plastic Plaster; Perforated Plastic Surgical Adhesive Tape; Perforated Plastic Self-adhesive Plaster

Permeable Plastic Surgical Adhesive Tape consists of an extensible perforated plastic film, spread evenly with an adhesive mass which does not offset when the tape is unrolled. The perforations are regularly distributed. The tape is permeable to water vapour and air. It is supplied wound on spools or cores.

The film may be coloured with a suitable pigment.

The tape complies with the requirements stated under Adhesive Tapes and with the following requirements.

Perforations Diameter, not more than 1 mm; area, not more than 20% of the total area of the film.

Water-vapour permeability Not less than 2000 g m⁻² per 24 hours, Appendix XX J1.

Weight of adhesive mass Not less than 25 g m⁻², Appendix XX D3, using Method III of Appendix XX D2.

Weight of film Not less than 60 g m⁻², Appendix XX D2, Method III.

Permeable Plastic Surgical Synthetic Adhesive Tape

Permeable Plastic Surgical Synthetic Adhesive Tape consists of an extensible perforated plastic film, spread evenly with a polymeric adhesive mass which does not offset when the tape is unrolled. The perforations are evenly distributed. The tape is permeable to water vapour and air. It is supplied wound on spools or cores.